

Product data YTONG-FIX P

Product description

Designed factory made thin joint mortar for autoclaved aerated concrete masonry blocks and panels for internal and external use in elements subject to structural and non structural requirements.

Composition

YTONG-fix P (Panels) thin joint mortar is specially designed for use with YTONG aerated concrete panels. YTONG-fix P is supplied dry and in pre-mixed 25kg bags.

The mortar has to be mixed for 4 minutes with the quantity of water state don the bag. This is to ensure that water can mix with all the cement particles. Afther mixing for 4 minutes a creamy mass should have been created with no dry mortar in the mix.

It remains workable within the bucket for approx. 4 hours

It will reach its initial bond strength within 7 to 10 minutes, and full design bond strength within 28 days.ed into an autoclave to be hardend.

Dry bulk density

1.425 +/- 75 kg/m³

Compressive strength

≥ 10,0 N/mm²

Initial shear strength

≥ 0,3 N/mm²

Chloride content

< 0,1 % m/m

Reaction to fire

Class A1

Water absorption

< 0,35 kg/m².min0,5

Water vapour permeability

5 / 20



Thermal conductivity

$\lambda = 0,52 \text{ W/mK}$

Durability (against freeze/thaw)

History has shown, that the mortar has a high freeze/thaw resistance when applied in the intended place of use.

Bond strength

≥ 0,30 N/mm²

Workable life :

≥ 4 hours

Correction time:

≥ 15 minutes



YTONG

Other information

Xella's technical staff are on hand to render assistance with written or telephone enquiries.

Xella UK

P.O Box 10028
Sutton Coldfield
United Kingdom B75 7ZF
Tel: +44 (0) 8432 909 080
Fax: +44 (0) 8432 909 081

E: silka-uk@xella.com
W: www.xella.co.uk